

Clyrell RC112L

PP RANDOM

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	7	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	18	MPa	ISO 527
Yield strain	15	%	ISO 527
Stress at Break	26	MPa	ISO 527
Strain at Break	680	%	ISO 527
Notched Impact Strength (Charpy), +23°C	13	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	450	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	55	°C	ISO 75-1/-2
Vicat softening temperature A	113	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion

Certifications

Food approval

Features

Copolymer, Random Copolymer

Applications

Packaging