

Hostacom TRC 482N E C12990
PP COPO-T22

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	20	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Flexural Modulus (23°C)	1750	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	40	kJ/m ²	ISO 180/1A
Notched Impact Strength (Izod)	3.5	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	106	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1040	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Impact modified, UV stablized

Features

Copolymer

Applications

Automotive