

Hostacom TRC 2157N C12509

PP COPO-T18

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	20	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Notched Impact Strength (Charpy), +23°C	40	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	3	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	1800	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	95	°C	ISO 75-1/-2
Vicat softening temperature A	130	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1030	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

UV stabilized

Features

Low Emission, Scratch Resistant, Copolymer

Applications

Automotive