

Hostacom TRC 411N C11515

PP COPO-T15

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	19	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Notched Impact Strength (Charpy), +23 °C	30	kJ/m ²	ISO 179/1eA
Flexural Modulus (23 °C)	1800	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	90	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1020	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

Impact modified, UV stablized

Features

Color Stability, Ductile, Low Emission, Low Odor, Scratch Resistant, Copolymer

Applications

Automotive