

Hostacom EKC 2040Y E BLACK

PP OTHERS-T20

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	13	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Notched Impact Strength (Charpy), +23°C	4	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	2500	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	105	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1050	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Low Emission, Low Odor

Delivery form

Black

Applications

Automotive