

Hostalen PP H2464

PP COPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	0.3	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	28	MPa	ISO 527
Yield strain	13	%	ISO 527
Notched Impact Strength (Charpy), +23°C	55	kJ/m ²	ISO 179/1eA

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing	Features
Sheet Extrusion, Other Extrusion, Pipe/Tube Extrusion	Copolymer, Impact Copolymer
Delivery form	Chemical Resistance
Natural Color	Oxidation Resistance
Special Characteristics	Certifications
Impact modified, Heat aging stabilized	Food approval, Food approval 1935/2004/EC, Food approval 10/2011, Food Contact (FDA)