

Moplen EP222D

PP COPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	0.9	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	26	MPa	ISO 527
Yield strain	14	%	ISO 527
Stress at Break	31	MPa	ISO 527
Strain at Break	500	%	ISO 527
Notched Impact Strength (Charpy), +23°C	70	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	1070	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	83	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	152	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion, Blow Molding, Blown Film Extrusion, Pipe/Tube Extrusion

Special Characteristics

Impact modified

Features

Good Adhesion, Heat Sealable, Copolymer, Impact Copolymer

Certifications

Food approval

Applications

Packaging