

Moplen EP340M

PP COPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	7.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1050	MPa	ISO 527
Yield stress	21	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	45	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness	46	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	80	°C	ISO 75-1/-2
Vicat softening temperature A	144	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Nucleated, Copolymer, Impact Copolymer

Special Characteristics

Impact modified

Applications

Sports Equipment