

Moplen EP3307

PP COPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	14	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	20	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at Break	15	MPa	ISO 527
Strain at Break	350	%	ISO 527
Notched Impact Strength (Charpy), +23°C	40	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	1100	MPa	ISO 178

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	163	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	90	°C	ISO 75-1/-2
Vicat softening temperature A	140	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	890	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

Impact modified, UV stablized

Features

High Crystallinity, Copolymer, Impact Copolymer

Applications

Automotive