

Moplen EP548V

PP COPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	100	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1450	MPa	ISO 527
Yield stress	28	MPa	ISO 527
Yield strain	5	%	ISO 527
Strain at Break	10	%	ISO 527
Notched Impact Strength (Charpy), +23°C	3.5	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	90	°C	ISO 75-1/-2
Vicat softening temperature A	152	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Certifications

Food approval

Special Characteristics

Anti-static, Opaque

Applications

Packaging, Sports Equipment

Features

Nucleated, Copolymer, Impact Copolymer