

## Moplen HP560Z

### PP HOMO

LyondellBasell Industries

Processing Method: Compounding; Continuous Filament/Spinning; Fibers; Melt Blown.

| Rheological properties | Value | Unit    | Test Standard |
|------------------------|-------|---------|---------------|
| ISO Data               |       |         |               |
| Melt Flow Index, MFI   | 1500  | g/10min | ISO 1133      |
| MFI temperature        | 230   | °C      | -             |
| MFI load               | 2.16  | kg      | -             |

### Characteristics

#### Processing

Other Extrusion

#### Features

Barrier Properties, Homopolymer

#### Delivery form

Pellets