

Moplen RP340N

PP RANDOM

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	11	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1150	MPa	ISO 527
Yield stress	30	MPa	ISO 527
Yield strain	14	%	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	6	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness	48	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	76	°C	ISO 75-1/-2
Vicat softening temperature A	130	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Gloss	135	-	ASTM D 2457
Haze	9	%	ASTM D 1003

Characteristics

Processing

Injection Molding

Special Characteristics

Transparent

Features

Nucleated, Copolymer, Random Copolymer

Certifications

Food approval

Applications

Packaging, Sports Equipment