

Purell HP373P

PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	18	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1250	MPa	ISO 527
Yield stress	31	MPa	ISO 527
Yield strain	15	%	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	6	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness	60	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	80	°C	ISO 75-1/-2
Vicat softening temperature A	150	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Haze	15	%	ASTM D 1003

Characteristics
Processing

Injection Molding

Chemical Resistance

Radiation Resistance

Special Characteristics

Transparent, Sterilizable, Ethylene Oxide (EtO) Sterilization, Steam sterilization, Gamma irradiation sterilization, Electron beam (e-beam) sterilization

Applications

Medical

Features

Homopolymer