

Purell HP572M
 PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	7.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1450	MPa	ISO 527
Yield stress	33	MPa	ISO 527
Yield strain	11	%	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	4.5	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness	64	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	85	°C	ISO 75-1/-2
Vicat softening temperature A	154	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics
Processing

Injection Molding, Film Extrusion, Blown Film Extrusion

Special Characteristics

Sterilizable, Ethylene Oxide (EtO) Sterilization, Steam sterilization

Features

Homopolymer

Applications

Medical, Packaging