

Softell TKG 317N E C11515
PP COPO-GF25

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	16	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt Flow Index, MFI	11	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Notched Impact Strength (Charpy), -30°C	5	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	4600	MPa	ISO 178

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1090	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Acoustical Barrier Properties, Low Odor, Scratch Resistant, Copolymer

Applications

Automotive