

Softell TKG 300N1 NAT

PP COPO-GF25

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	6	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Notched Impact Strength (Charpy), +23°C	35	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	7.5	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	2500	MPa	ISO 178

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1090	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Features

Scratch Resistant, Copolymer