

Purell HP570M

PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	7.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	31	MPa	ISO 527
Yield strain	10	%	ISO 527
Strain at Break	50	%	ISO 527
Impact Strength (Charpy), +23°C	133	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	3.5	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	83	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	82	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Homopolymer

Certifications

Medical, Biocompatibility ISO 10993, US Pharmacopeia Class VI
Approved, Drug Master File

Applications

Medical