

PS 3122

PS

MBA Polymers

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	6	g/10min	ISO 1133
MFI temperature	200	°C	-
MFI load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	24	MPa	ISO 527
Flexural Modulus (23°C)	2000	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	8	kJ/m ²	ISO 180/1A

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1040	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	1 - 2	h	-
Melt temperature	190 - 240	°C	-
Mold temperature	20 - 80	°C	-

Characteristics

Processing

Injection Molding

Certifications

Recycled Resin Content

Special Characteristics

Impact modified

Applications

General Purpose