

Ultrason® P 3010 MR SW 10101
PPSU

BASF

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	35	cm³/10min	ISO 1133
Temperature	360	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2270	MPa	ISO 527
Yield stress	74	MPa	ISO 527
Yield strain	7.8	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	no break	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	60	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	24	kJ/m²	ISO 179/1eA
Ball Indentation Hardness	124	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Glass Transition Temperature (10°C/min)	220	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	196	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	55	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-0	class	UL 94
Thickness tested	1.6	mm	-
Burning Behav. at thickness h	V-0	class	UL 94
Thickness tested	3.0	mm	-

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	1.2	%	Sim. to ISO 62
Humidity absorption	0.6	%	Sim. to ISO 62
Density	1290	kg/m³	ISO 1183

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	71	cm³/g	ISO 307, 1157, 1628

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Delivery form

Pellets, Black

Chemical Resistance

General Chemical Resistance