

ECOTRAN® N200

PPS

HDC Polyall

Melt viscosity (poise): 1500 - 2100

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	280	°C	ISO 11357-1/-3