

Hifax CA 7201 A

TPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	11	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield strain	13	%	ISO 527
Stress at Break	16	MPa	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	50	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	750	MPa	ISO 178
ASTM Data			
Tensile Strength at Yield	17	MPa	ASTM D 638

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	163	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	65	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	890	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Good Adhesion

Delivery form

Pellets, Natural Color

Applications

Automotive

Special Characteristics

Impact modified