

Softell CA 7413 A

TPO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	2.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Stress at Break	8	MPa	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	no break	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	30	MPa	ISO 178
Shore Hardness A (15s)	75	-	ISO 868

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	142	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	38	°C	ISO 75-1/-2
Vicat softening temperature A	41	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	880	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Sheet Extrusion, Other Extrusion, Blow Molding, Calendering

Delivery form

Pellets, Natural Color

Special Characteristics

Impact modified

Features

Soft Feel

Certifications

Food approval, Food approval 1935/2004/EC, Food approval 10/2011, Food Contact (FDA)

Applications

Automotive, Building Construction