

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tear strength	18	kN/m	ISO 34-1
Abrasion resistance	300	mm ³	ISO 4649
Shore Hardness A (15s)	28	-	ISO 868
Tensile Strength	4.4	MPa	ISO 37
Strain at Break	860	%	ISO 37
Stress at 100% Elongation	0.7	MPa	ISO 37
Stress at 300% Elongation	4.2	MPa	ISO 37

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1000	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding