

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	86	%	ISO 815
Compression Set under constant strain, 100 °C	92	%	ISO 815
Shore Hardness A (15s)	49	-	ISO 868
Tensile Strength	4	MPa	ISO 37
Strain at Break	468	%	ISO 37
Stress at 100% Elongation	1.8	MPa	ISO 37
Stress at 300% Elongation	10.5	MPa	ISO 37
Tear strength	22	kN/m	ISO 6383
Abrasion resistance	216	mm ³	DIN 53516

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	930	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding