

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	87	%	ISO 815
Compression Set under constant strain, 100 °C	99	%	ISO 815
Shore Hardness A (15s)	60	-	ISO 868
Tensile Strength	4.1	MPa	ISO 37
Strain at Break	363	%	ISO 37
Stress at 100% Elongation	2.7	MPa	ISO 37
Stress at 300% Elongation	12	MPa	ISO 37
Tear strength	26	kN/m	ISO 6383
Abrasion resistance	347	mm ³	DIN 53516

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1080	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding