

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tear strength	21	kN/m	ISO 34-1
Abrasion resistance	400	mm ³	ISO 4649
Shore Hardness A (15s)	35	-	ISO 868
Tensile Strength	3.3	MPa	ISO 37
Strain at Break	910	%	ISO 37
Stress at 100% Elongation	1.2	MPa	ISO 37
Stress at 300% Elongation	5.1	MPa	ISO 37

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1000	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding