

Evoprene® COGEE 631 TPE

Alphagary

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	89	%	ISO 815
Compression Set under constant strain, 100 °C	89	%	ISO 815
Shore Hardness A (15s)	50	-	ISO 868
Tensile Strength	3.6	MPa	ISO 37
Strain at Break	315	%	ISO 37
Stress at 100% Elongation	2.2	MPa	ISO 37
Stress at 300% Elongation	11.1	MPa	ISO 37
Tear strength	24	kN/m	ISO 6383
Abrasion resistance	271	mm ³	DIN 53516

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1050	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding