

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	50	%	ISO 815
Compression Set under constant strain, 100 °C	68	%	ISO 815
Shore Hardness A (15s)	85	-	ISO 868
Tensile Strength	12.3	MPa	ISO 37
Strain at Break	724	%	ISO 37
Stress at 100% Elongation	5	MPa	ISO 37
Stress at 300% Elongation	19.5	MPa	ISO 37
Tear strength	54.7	kN/m	ISO 6383

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	890	kg/m³	ISO 2781

Characteristics

Processing

Injection Molding