

Evoprene® GC 5688 TPE

Alphagary

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	34	%	ISO 815
Compression Set under constant strain, 100 °C	61	%	ISO 815
Shore Hardness A (15s)	51	-	ISO 868
Tensile Strength	4.6	MPa	ISO 37
Strain at Break	675	%	ISO 37
Stress at 100% Elongation	1.5	MPa	ISO 37
Stress at 300% Elongation	6.9	MPa	ISO 37
Tear strength	20	kN/m	ISO 6383
Abrasion resistance	280	mm ³	DIN 53516

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	880	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding