

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	52	%	ISO 815
Compression Set under constant strain, 100 °C	76	%	ISO 815
Shore Hardness A (15s)	83	-	ISO 868
Tensile Strength	9.7	MPa	ISO 37
Strain at Break	558	%	ISO 37
Stress at 100% Elongation	4.85	MPa	ISO 37
Stress at 300% Elongation	18.7	MPa	ISO 37
Tear strength	47.3	kN/m	ISO 6383

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	880	kg/m³	ISO 2781

Characteristics

Processing

Injection Molding