

Pebax® 7233 SA 01 MED

TPA

ARKEMA

Polyether block amide **Pebax® 7233 SA 01 MED resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Pebax® 7233 SA 01 MED resin also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response.

Upon request, letters regarding USP Class VI compliance can be provided.

Main applications:

- Tubings like angiography and angioplasty catheters
- Flexible injected parts

Packaging:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.1 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	- / 510	MPa	ISO 527
Yield stress	- / 26	MPa	ISO 527
Yield strain	- / 18	%	ISO 527
Nominal strain at break	- / >50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	- / 15	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	- / 10	kJ/m²	ISO 179/1eA
Shore Hardness D (15s)	61 / -	-	ISO 868

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	174 / *	°C	ISO 11357-1/-3
Vicat softening temperature, 50°C/h 50N	106 / *	°C	ISO 306

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	0.9 / *	%	Sim. to ISO 62
Humidity absorption	0.7 / *	%	Sim. to ISO 62
Density	1010 / -	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70 - 80	°C	-
Pre-drying - Time	5 - 7	h	-
Melt temperature	230 - 290	°C	-
Mold temperature	25 - 60	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

Light stabilized or stable to light, Heat aging stabilized

Delivery form

Pellets

Certifications

Medical, US Pharmacopeia Class VI Approved

Injection Molding

Pebax® 7233 SA 01 MED

TPA

ARKEMA

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C.
- Typical mold temperature : 25 – 60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C.

Other Extrusion

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 220°C / 235°C / 250°C.
 - Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C.
-