

## Pebax® 4033 SA 01 MED

TPA

ARKEMA

Polyether block amide **Pebax® 4033 SA 01 MED** resin is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices. Upon request, letters regarding USP Class VI compliance can be provided.

### Main applications:

- Catheters
- Flexible injected parts

### Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

### Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

机械性能	干 / 湿	单位	试验方法
ISO数据			
拉伸模量	73 / 71	MPa	ISO 527
50%伸长率时的应力S	9 / 9	MPa	ISO 527
断裂伸长率	>50 / >50	%	ISO 527
肖氏硬度A, 3s	89 / -	-	ISO 868
肖氏硬度D, 15s	35 / -	-	ISO 868

热性能	干 / 湿	单位	试验方法
ISO数据			
熔融温度, 10°C/min	160 / *	°C	ISO 11357-1/-3

其它性能	干 / 湿	单位	试验方法
ISO数据			
吸水性	1.2 / *	%	类似ISO 62
吸湿性	0.5 / *	%	类似ISO 62
密度	1000 / 1000	kg/m³	ISO 1183

加工推荐 (注塑)	数值	单位	试验方法
预干燥-温度	60 - 70	°C	-
预干燥-时间	4 - 6	h	-
注塑熔体温度	200 - 270	°C	-
模具温度	10 - 30	°C	-

### 特征

#### 加工方法

注塑, 其它挤出成型

#### 特殊性能

经光稳处理的/耐光的, 经热稳处理的/耐热的

#### 供货形式

粒料

#### 生态估价

医用级, US药物六级认证

### 注塑

#### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 200°C / 240°C / 270°C.
- Typical mold temperature : 10 – 30°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 60-70°C.

### 其它挤出成型

#### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 60-70°C.