

K-Resin® SKR18
SB

INEOS Styrolution

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	14	g/10min	ISO 1133
MFI temperature	200	°C	-
MFI load	5	kg	-

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1010	kg/m³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Copolymer

Additives

Release agent