

| Mechanical Properties                        | Value | Unit | Test Standard |
|----------------------------------------------|-------|------|---------------|
| ISO Data                                     |       |      |               |
| Compression Set under constant strain, 70 °C | 30    | %    | ISO 815       |
| Tear strength                                | 19    | kN/m | ISO 34-1      |
| Shore Hardness A (15s)                       | 65    | -    | ISO 868       |
| Tensile Strength                             | 6.1   | MPa  | ISO 37        |
| Strain at Break                              | 400   | %    | ISO 37        |

| Other Properties | Value | Unit  | Test Standard |
|------------------|-------|-------|---------------|
| ISO Data         |       |       |               |
| Density          | 900   | kg/m³ | ISO 1183      |

Characteristics

| Processing        | Features    |
|-------------------|-------------|
| Injection Molding | Low Fogging |