

Evoprene® G TS 6131 SEBS

Alphagary

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 70 °C	34	%	ISO 815
Compression Set under constant strain, 100 °C	56	%	ISO 815
Shore Hardness A (15s)	47	-	ISO 868
Tensile Strength	10.3	MPa	ISO 37
Strain at Break	634	%	ISO 37
Stress at 100% Elongation	1.3	MPa	ISO 37
Stress at 300% Elongation	7.8	MPa	ISO 37
Tear strength	21	kN/m	ISO 6383
Abrasion resistance	379	mm ³	DIN 53516

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 2781

Characteristics

Processing

Injection Molding