

Luran® KR2635 UN
SAN

INEOS Styrolution

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	200	°C	-
Load	5	kg	-

Other Properties	Value	Unit	Test Standard
ISO Data			
Bulk density	600	kg/m ³	-

Characteristics

Delivery form

Pellets, Natural Color

Features

Copolymer