



Desmopan 9380A

TPU

Covestro Deutschland AG

- Extrusion- and injection molding grade
- very good hydrolysis and microbial resistance
- good low-temperature flexibility
- complies with VDE 0282-10

Application:

- Cable sheathings
- Hoses, non-reinforced


Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Stress (10% Elongation)	1.5	MPa	ISO 527
Stress at 100% Elongation	5.3	MPa	ISO 527
Stress at 300% Elongation	9	MPa	ISO 527
Stress at Break TPE	43	MPa	ISO 527
Strain at Break TPE	>300	%	ISO 527
Compression Set under constant strain, 70 °C	40	%	ISO 815
Tear strength	50	kN/m	ISO 34-1
Abrasion resistance	25	mm ³	ISO 4649
Shore Hardness A (15s)	80	-	ISO 868
Shore Hardness D (15s)	31	-	ISO 868

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1110	kg/m ³	ISO 1183


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	1 - 2	h	-
Processing humidity	≤0.05	%	-
Melt temperature	200 - 230	°C	-
Mold temperature	20 - 40	°C	-

Diagrams

Viscosity-shear rate



Shearstress-shear rate




Desmopan 9380A

TPU

Covestro Deutschland AG

Stress-Strain (TPE)



Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion

Injection Molding

PREPROCESSING

Max. water content: 0.05 %
Max. drying temperature: 80 °C
Drying time:
Dry air dryer 1-2 h

PROCESSING

Melt temperature: 200-230 °C
Mold temperature: 20-40 °C

Other Extrusion

Preprocessing	
Max. Water content	≤0.05 %
Drying temperature	70-110 °C
Dry air dryer	1-2 h
Processing	
Melt temperature	195-215 °C

Profile extrusion

Preprocessing	
Max. Water content	≤0.05 %
Drying temperature	70-110 °C
Dry air dryer	1-2 h
Processing	
Melt temperature	180-210 °C