+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





## Evoprene™ COGEE 5845 TPS

**Alphagary** 

Note: mechanical properties were originally reported according to ISO 37. Comparison with data according ISO 527 seems to be acceptable in this case.

Service Temp Guide = -40 to +100 °C

Thermoplastic compatibility: PC, ABS, PA

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5	MPa	ISO 527
Stress at 100% Elongation	2	MPa	ISO 527
Strain at Break TPE	>300	%	ISO 527
Compression Set under constant strain, 23°C	30	%	ISO 815
Compression Set under constant strain, 70°C	66	%	ISO 815
Tear strength	29	kN/m	ISO 34-1
Shore Hardness A (15s)	60	-	ISO 868

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1180	kg/m³	ISO 1183

## Characteristics

Processing Injection Molding **Chemical Resistance** 

Ozone Resistance