



Texin® RxS285

TPU

Covestro Deutschland AG

Rheological properties	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Melt Flow Index, MFI	4	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	8.7	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Flexural Modulus (23°C)	27.6	MPa	ISO 178
Stress at 100% Elongation	5.34	MPa	ISO 527
Stress at 300% Elongation	13.1	MPa	ISO 527
Tear strength	87.6	kN/m	ISO 34-1
Shore Hardness A (15s)	85	-	ISO 868
Tensile Strength	37.9	MPa	ISO 37
Strain at Break	500	%	ISO 37

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature A	91	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1200	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82 - 99	°C	-
Pre-drying - Time	≥2	h	-
Processing humidity	≤0.03	%	-
Melt temperature	196 - 207	°C	-
Mold temperature	16 - 43	°C	-
Zone 1	182 - 199	°C	-
Zone 2	182 - 204	°C	-
Zone 3	182 - 210	°C	-
Nozzle temperature	188 - 213	°C	-
Screw speed	40 - 80	rpm	-
Injection pressure	41.4 - 103	MPa	-
Back pressure	≤5.5	MPa	-
Holding pressure	24.8 - 82.7	MPa	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	82 - 99	°C	-
Pre-drying - Time	≥2	h	-
Processing humidity	≤0.03	%	-
Melt temperature	191 - 204	°C	-
Feed temperature	182 - 199	°C	-
Zone 1	182 - 204	°C	-
Zone 2	182 - 210	°C	-
Nozzle temperature	188 - 210	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion, Blow Molding, Pipe/Tube Extrusion

Delivery form

Natural Color

Chemical Resistance

Radiation Resistance

Certifications

Medical, Biocompatibility ISO 10993, Food approval, Food Contact (FDA)

Texin® RxS285
TPU

Covestro Deutschland AG

Special Characteristics

Impact modified, Heat aging stabilized, Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization

Applications

Medical