+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)





Evoprene™ 3276 TPS

Note: mechanical properties were originally reported according to ISO 37. Comparison with data according ISO 527 seems to be acceptable in this case.

Service Temp Guide = -50 to +50 °C

Thermoplastic compatibility: PS

机械性能	数值	单位	试验方法	
ISO数据				
拉伸强度	4.6	MPa	ISO 527	
100%应变时的应力	1	MPa	ISO 527	
断裂应变. TPE	>300	%	ISO 527	
时恒定应变下的永久变形, 23°C	39	%	ISO 815	
撕裂强度	16	kN/m	ISO 34-1	
肖氏硬度A, 3s	33	-	ISO 868	

其它性能	数值	单位	试验方法	
ISO数据				
密度	970	kg/m³	ISO 1183	

加工方法 注塑

特殊性能

透明.