



## Solplast TH 35A7000 A

### TPS

Uteksol d.o.o.

| Rheological properties | Value | Unit    | Test Standard |
|------------------------|-------|---------|---------------|
| <b>ISO Data</b>        |       |         |               |
| Melt Flow Index, MFI   | 13    | g/10min | ISO 1133      |
| MFI temperature        | 190   | °C      | -             |
| MFI load               | 5     | kg      | -             |

| Mechanical Properties                       | Value | Unit | Test Standard |
|---------------------------------------------|-------|------|---------------|
| <b>ISO Data</b>                             |       |      |               |
| Compression Set under constant strain, 23°C | 15    | %    | ISO 815       |
| Compression Set under constant strain, 70°C | 90    | %    | ISO 815       |
| Tear strength                               | 15    | kN/m | ISO 34-1      |
| Shore Hardness A (15s)                      | 35    | -    | ISO 868       |
| Tensile Strength                            | 2.8   | MPa  | ISO 37        |
| Strain at Break                             | 580   | %    | ISO 37        |

| Other Properties | Value | Unit  | Test Standard |
|------------------|-------|-------|---------------|
| <b>ISO Data</b>  |       |       |               |
| Density          | 1040  | kg/m³ | ISO 1183      |

| Processing Recommendation Injection Molding | Value     | Unit | Test Standard |
|---------------------------------------------|-----------|------|---------------|
| Melt temperature                            | 160 - 220 | °C   | -             |
| Mold temperature                            | 30 - 40   | °C   | -             |

## Characteristics

### Processing

Injection Molding

### Features

Copolymer