



## Solplast TH 40A9000 C1 TPS

Uteksol d.o.o.

| Rheological properties | Value | Unit    | Test Standard |
|------------------------|-------|---------|---------------|
| <b>ISO Data</b>        |       |         |               |
| Melt Flow Index, MFI   | 2.5   | g/10min | ISO 1133      |
| MFI temperature        | 190   | °C      | -             |
| MFI load               | 5     | kg      | -             |

| Mechanical Properties                        | Value | Unit | Test Standard |
|----------------------------------------------|-------|------|---------------|
| <b>ISO Data</b>                              |       |      |               |
| Compression Set under constant strain, 23°C  | 14    | %    | ISO 815       |
| Compression Set under constant strain, 70°C  | 37    | %    | ISO 815       |
| Compression Set under constant strain, 100°C | 56    | %    | ISO 815       |
| Tear strength                                | 16    | kN/m | ISO 34-1      |
| Shore Hardness A (15s)                       | 40    | -    | ISO 868       |
| Tensile Strength                             | 5.5   | MPa  | ISO 37        |
| Strain at Break                              | 890   | %    | ISO 37        |

| Other Properties | Value | Unit  | Test Standard |
|------------------|-------|-------|---------------|
| <b>ISO Data</b>  |       |       |               |
| Density          | 1160  | kg/m³ | ISO 1183      |

### Characteristics

#### Processing

Other Extrusion

#### Features

Copolymer