



Solplast TH 75A9000 C0

TPS

Uteksol d.o.o.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	3.2	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 23°C	22	%	ISO 815
Compression Set under constant strain, 70°C	39	%	ISO 815
Compression Set under constant strain, 100°C	63	%	ISO 815
Tear strength	30	kN/m	ISO 34-1
Shore Hardness A (15s)	75	-	ISO 868
Tensile Strength	11	MPa	ISO 37
Strain at Break	860	%	ISO 37

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	980	kg/m³	ISO 1183

Characteristics

Processing

Other Extrusion

Features

Copolymer