

Solplast TH 90A9000 C1 TPS

Uteksol d.o.o.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	3.3	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Compression Set under constant strain, 23°C	37	%	ISO 815
Compression Set under constant strain, 70°C	51	%	ISO 815
Compression Set under constant strain, 100°C	73	%	ISO 815
Tear strength	34	kN/m	ISO 34-1
Shore Hardness A (15s)	90	-	ISO 868
Tensile Strength	11.3	MPa	ISO 37
Strain at Break	710	%	ISO 37

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1160	kg/m³	ISO 1183

Characteristics

Processing

Other Extrusion

Features

Copolymer