

AF312A

Description

AF312A is an ABS product apply for injection molding, with 1.5mm V-0 flame retardancy and high flow

Key Features

Opacity, High Flame Retardancy,
Hot Stamping, Paintability, Dimensional
Stability, High Flow

Application

Switch panel, socket, Charge, electric
control box

Plant

China(Huizhou)

| Properties | Condition | Method | Unit | AF312A |
|-----------------------------|--------------------------------------|------------|---------|--------|
| Physical | | | | |
| Melt Flow Index | 220°C, 10kg | ASTM D1238 | g/10min | 53 |
| Mechanical | | | | |
| Tensile Strength at Yield | 23°C, 50mm/min, 3.2mm | ASTM D638 | MPa | 43 |
| Flexural Strength | 23°C, 10mm/min, 6.4mm | ASTM D790 | MPa | 60 |
| Flexural Modulus | 23°C, 10mm/min, 6.4mm | ASTM D790 | MPa | 2230 |
| Izod Impact Strength | Notched, 6.4mm, 23°C | ASTM D256 | J/m | 21 |
| Rockwell Hardness | R-Scale | ASTM D785 | | 101 |
| Thermal | | | | |
| Heat Deflection Temperature | Edgewise, 1.82MPa, 6.4mm, Unannealed | ASTM D648 | °C | 84 |

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

AF312A

Description

AF312A is an ABS product apply for injection molding, with 1.5mm V-0 flame retardancy and high flow

Key Features

Opacity, High Flame Retardancy,
Hot Stamping, Paintability, Dimensional
Stability, High Flow

Application

Switch panel, socket, Charge, electric
control box

Plant

China(Huizhou)

Processing Guide (Injection Molding)

| Processing Parameters | Unit | Value |
|-----------------------|------|---------|
| Drying Temperature | °C | 70~80 |
| Drying Time | hrs | 2~4 |
| Injection Temperature | °C | 190~230 |
| Mold Temperature | °C | 40~70 |
| Screw Speed | rpm | 30~60 |

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.