+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

## Solution**Partner**



# AF365S

## **Description**

AF365S is a Flame Retardant ABS product for extrusion and blow molding, designed to have a flammability rating of V-0 at 2.0mm.

## **Key Features**

## **Application**

Flame Retardancy

**Battery Tray** 

| Properties                  | Condition                            | Method     | Unit     | AF365S    |
|-----------------------------|--------------------------------------|------------|----------|-----------|
| Physical                    |                                      |            |          |           |
| Specific Gravity            | 23°C                                 | ASTM D792  |          | 1.16      |
| Mold Shrinkage              | 23°C, 3.2mm                          | ASTM D955  | %        | 0.4 ~ 0.7 |
| Melt Flow Index             | 220°C, 10kg                          | ASTM D1238 | g/10min  | 7.5       |
| Mechanical                  |                                      |            |          |           |
| Tensile Strength at Yield   | 23°C, 50mm/min, 3.2mm                | ASTM D638  | MPa      | 47        |
| Tensile Elongation at Yield | 23°C, 50mm/min, 3.2mm                | ASTM D638  | %, (Min) | 5         |
| Tensile Elongation at Break | 23°C, 50mm/min, 3.2mm                | ASTM D638  | %, (Min) | 15        |
| Flexural Strength           | 23°C, 10mm/min, 6.4mm                | ASTM D790  | MPa      | 77        |
| Flexural Modulus            | 23°C, 10mm/min, 6.4mm                | ASTM D790  | MPa      | 2550      |
| Izod Impact Strength        | Notched, 3.2mm, 23°C                 | ASTM D256  | J/m      | 290       |
| Izod Impact Strength        | Notched, 6.4mm, 23°C                 | ASTM D256  | J/m      | 200       |
| Rockwell Hardness           | R-Scale                              | ASTM D785  |          | 108       |
| Thermal                     |                                      |            |          |           |
| Heat Deflection Temperature | Edgewise, 1.82MPa, 6.4mm, Unannealed | ASTM D648  | °C       | 87        |
| Flammability                | 1.7mm                                | UL 94      |          | V-1       |
| Flammability                | 2.0mm                                | UL 94      |          | V-0, 5VA  |
| Flammability                | 2.5mm                                | UL 94      |          | V-0, 5VA  |
| Flammability                | 3.0mm                                | UL 94      |          | V-0, 5VA  |

#### **Note**

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

## Solution**Partner**



## AF365S

## **Description**

AF365S is a Flame Retardant ABS product for extrusion and blow molding, designed to have a flammability rating of V-0 at 2.0mm.

## **Key Features**

**Application** 

Flame Retardancy

**Battery Tray** 

## Processing Guide (Extrusion)

| <b>Processing Parameters</b> | Unit | Value     |
|------------------------------|------|-----------|
| Drying Temperature           | °C   | 70 ~ 80   |
| Drying Time                  | hrs  | 3 ~ 4     |
| Moisture Content             | %    | ~ 0.01    |
| Extrusion Temperature        | °C   | 200 ~ 230 |

#### **Note**

Recommend initial lower temperatures settings to avoid material degradation/hang-up in die & Damp; purge material from extruder prior to shutdown.