

CRI571M2H

Description

CRI571M2H is a transparent PCR ABS product for injection molding, containing 20% PCR recycled resin. It is designed as an injection molding product with semi-transparent characteristics, high fluidity, and gloss.

Key Features

Transparency, Recycled ABS (PCR 20%)

Application

Electric/electronic products

Properties	Condition	Method	Unit	CRI571M2H
Physical				
Specific Gravity	23°C	ASTM D792		1.07
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	53
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	47
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	10 ~
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	72
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2600
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	15 ~
Rockwell Hardness	R-Scale	ASTM D785		110
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	83
Flammability	1.5mm	UL 94		HB
Flammability	3.0mm	UL 94		HB

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

CRI571M2H

Description

CRI571M2H is a transparent PCR ABS product for injection molding, containing 20% PCR recycled resin. It is designed as an injection molding product with semi-transparent characteristics, high fluidity, and gloss.

Key Features

Transparency, Recycled ABS (PCR 20%)

Application

Electric/electronic products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	3 ~ 4
Injection Temperature	°C	200 ~ 230
Mold Temperature	°C	40 ~ 60
Screw Speed	rpm	30 ~ 60

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.