

MRC365L5

Description

MRC365L5, a Flame Retardant Post-Consumer Recycled ABS product for injection molding, contains 50% PCR resin and is designed to carry out light colors with the same physical properties as standard FR ABS, flammability rating of V-0 at 2.0mm. (Early stage of development : The data can be changed as a result of the quality improvement of the products)

Key Features

Flame Retardancy, Recycled ABS (PCR 50%)

Application

Batter Case, PCB Case, Electrical/Electronic Products

Properties	Condition	Method	Unit	MRC365L5
Physical				
Specific Gravity	23°C	ASTM D792		1.17
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	30
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	370
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	15 ~
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	59
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2100
Izod Impact Strength	Notched, 3.2mm, 23°C	ASTM D256	J/m	230
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	140
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	82
Flammability	2.0mm	UL 94		V-0
Flammability	3.0mm	UL 94		V-0

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

MRC365L5

Description

MRC365L5, a Flame Retardant Post-Consumer Recycled ABS product for injection molding, contains 50% PCR resin and is designed to carry out light colors with the same physical properties as standard FR ABS, flammability rating of V-0 at 2.0mm. (Early stage of development : The data can be changed as a result of the quality improvement of the products)

Key Features

Flame Retardancy, Recycled ABS (PCR 50%)

Application

Batter Case, PCB Case, Electrical/Electronic Products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	3 ~ 4
Injection Temperature	°C	200 ~ 230
Mold Temperature	°C	40 ~ 80
Screw Speed	rpm	30 ~ 60

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.