

LI925

Description

LI925 is an ASA product for extrusion and calendering, designed to have good weatherability and chemical resistance, and high impact strength.

Key Features

Weatherability, Chemical Resistance, High Impact Strength,
High Elongation

Application

Deco Sheet, Handrail

Properties	Condition	Method	Unit	LI925
Physical				
Specific Gravity	23°C	ASTM D792		1.07
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	6
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	31
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	100
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	45
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	1300
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	340
Rockwell Hardness	R-Scale	ASTM D785		75
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	80

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

LI925

Description

LI925 is an ASA product for extrusion and calendering, designed to have good weatherability and chemical resistance, and high impact strength.

Key Features

Weatherability, Chemical Resistance, High Impact Strength,
High Elongation

Application

Deco Sheet, Handrail

Processing Guide (Extrusion)

Processing Parameters	Unit	Value
Drying Temperature	°C	80 ~ 90
Drying Time	hrs	3 ~ 4
Moisture Content	%	~ 0.01
Extrusion Temperature	°C	180 ~ 250

Note

Recommend initial lower temperatures settings to avoid material degradation/hang-up in die & purge material from extruder prior to shutdown.