

LI965

Description

LI965 is an ASA product for extrusion and thermoforming, designed to have chemical resistance to HCFC-141b & HFC-245fa foaming agents.

Key Features

Thermoforming, Chemical Resistance to HCFC & HFC, High Impact Strength

Application

Refrigerator

Properties	Condition	Method	Unit	LI965
Physical				
Specific Gravity	23°C	ASTM D792		1.05
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	4.5
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	44
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	20
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	70
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2100
Izod Impact Strength	Notched, 3.2mm, 23°C	ASTM D256	J/m	280
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	260
Rockwell Hardness	R-Scale	ASTM D785		101
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	88
Vicat Softening Temperature	50N, 50°C/h	ASTM D1525	°C	95

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

LI965

Description

LI965 is an ASA product for extrusion and thermoforming, designed to have chemical resistance to HCFC-141b & HFC-245fa foaming agents.

Key Features

Thermoforming, Chemical Resistance to HCFC & HFC, High Impact Strength

Application

Refrigerator

Processing Guide (Extrusion)

Processing Parameters	Unit	Value
Drying Temperature	°C	80 ~ 90
Drying Time	hrs	3 ~ 4
Moisture Content	%	~ 0.01
Extrusion Temperature	°C	180 ~ 250

Note

Recommend initial lower temperatures settings to avoid material degradation/hang-up in die & purge material from extruder prior to shutdown.